



Protac Scribe™ UV 62μ (2.4 mil)


Product Description

Protac Scribe™ 62μ (2.4 mil) is a 40μ (1.6 mil) gloss finish, biaxially oriented overlaminating film coated on one side with a pressure sensitive, solvent acrylic adhesive, which is protected by a bleached Kraft release paper (moisture stable) coated on both sides with polyethylene and siliconised on the release side. Available in various sizes.

Suggested Applications

Protac Scribe™ cold laminating film is ideally suited for application to heat-sensitive output and high ink coverage prints printed on photo gloss paper. The most common demands for these products are for reusable presentation boards, schedules, year planners and maps.

Product Structure

Film:	Dry-erase/gloss film	
Adhesive:	Solvent Acrylic (Pressure Sensitive)	
Release Liner:	2 Side PE Coated Bleached Woodfree Paper (Moisture Stable)	

General Properties

Film Thickness	40μ (1.6 mil)
Adhesive Layer	22μ (1mil)
Ratio Film/Adhesive	1.8/1
UV Protection Factor	Film contains some U.V. stabilisers, which prevent film degradation, can be used for short term external use (3 months)

Heat resistance	110oC to 120oC (230oF to 248oF)
Peel Strength (20 min, FTM1)	12 N/25mm

Process Settings

Roller Laminator	Press
Temperature: Room temperature to 49°C (120°F) Speed: 0.3m to 2.1m (1 ft to 7 ft) per minute	NOT RECOMMENDED

Specifications subject to change without notice.

Published information concerning Drytac products is based upon research which the company believes to be reliable and accurate. Such information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Drytac does not accept liability for risks associated with the performance of the materials in application. All Drytac products are subjected to carefully quality control throughout the manufacturing process and are sold subject to Drytac standard conditions of sale

Drytac Europe Ltd (UK) – Drytac House, Filwood Road, Fishponds, Bristol, BS16 3RY, UK. Tel: +44 (0) 845-070-0660
Drytac Corp. (USA) – 5601 Eastport Blvd., Richmond, Virginia 23231, USA. Telephone: 1-800-603-6610
Drytac Canada Inc. (Canada) – 220 Caldari Road, Concord, Ontario, L4K 3X5, Canada. Telephone: 1-800-353-288